

4.1 Zinc with Impurities		Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Sb	As	Bi	In	Tl	Ti	Cr	Ag	Size	
CRM	C41 X Z10M	0.0018	(0.0003)	(0.00015)	0.00005	0.0005	<0.0002	0.0005	0.00010	0.00018	(0.0004)	...	...	<0.00005	(0.0003)	...	...	...	50g	
CRM	C41 X Z30K	0.0052	0.0009	0.0083	0.0044	0.002	0.0039	0.0019	0.0031	0.0007	0.0037	...	...	0.0007	0.002	0.0012	...	...	50g	
CRM	C41 X Z40K	0.0092	0.0019	0.0096	0.0066	0.003	0.0070	0.0047	0.0069	0.0012	0.005	...	...	0.0015	0.003	<0.0005	...	...	50g	
CRM	C41 X Z50L	0.0235	0.012	0.142	0.024	(0.015)	0.0213	0.0228	0.0116	0.0033	0.006	...	...	0.004	0.0032	...	...	...	50g	
CRM	C41 X 0336 Z10K	0.95	0.0049	0.014	0.0056	0.0124	0.005	0.007	(0.0006)	0.0035	...	...	...	...	...	...	...	...	50g	
CRM	C41 X 0336 Z30J	0.019	0.134	0.43	0.341	0.270	0.111	0.361	...	0.0058	...	...	...	...	...	...	...	...	50g	
CRM	C41 X 0336 Z40B	2.87	0.179	1.39	0.638	(0.018)	2.38	0.874	0.0074	0.038	0.048	0.0005	0.027	0.0035	(0.004)	...	...	0.0023	50g	
CRM	C41 X 0336 Z50A	0.91	<0.0005	0.035	0.056	0.016	0.21	0.023	(0.0005)	(0.0001)	0.008	...	(0.001)	...	...	...	...	...	50g	
CRM	C41 X 0336 Z60A	1.82	0.0008	0.105	0.014	0.08	0.0023	0.0203	0.0018	0.0010	0.234	0.0020	0.123	0.0123	0.0132	...	...	0.0055	50g	
CRM	C41 X 4380 Z10C	0.068	0.0012	0.055	0.376	0.01	0.049	0.175	0.0029	0.0015	0.002	...	0.0017	...	...	(0.001)	0.002	...	50g	
CRM	C41 X 4380 Z40C	0.325	0.126	0.144	0.094	0.056	0.038	0.0022	0.0040	0.0007	0.017	...	0.011	...	...	0.005	(0.0003)	...	50g	
CRM	C41 X 4380 Z70C	1.25	0.0028	0.137	0.015	(0.0044)	0.0047	0.012	0.012	...	0.090	...	...	...	...	0.009	0.0045	...	50g	
CRM	C41 X 4380 Z80C	0.73	0.007	0.225	0.0079	0.003	0.011	0.020	0.024	0.0015	0.016	...	0.011	...	...	0.012	0.0019	...	50g	
CRM	C41 X 2951 Z10	0.0042	0.0029	0.029	0.0005	0.011	(0.0007)	0.79	0.0038	0.0013	...	...	...	...	...	0.278	0.083	...	50g	
CRM	C41 X 2951 Z30	0.0065	0.0164	0.078	0.0062	0.029	(0.006)	1.89	0.0010	0.0018	...	...	...	...	...	0.133	0.184	...	50g	
																			<b>Co</b>	
CRM	C41 X GLV10A	0.056	...	0.115	0.0093	0.059	0.010	0.0028	0.0141	...	<0.001	<0.001	0.0025	...	...	...	...	...	50g	
CRM	C41 X GLV20A	0.214	...	0.068	0.0025	0.048	0.003	0.0052	0.0070	...	0.006	<0.001	0.017	...	...	...	...	...	50g	
CRM	C41 X GLV30A	0.0080	...	0.31	0.021	0.012	0.006	0.0188	0.0301	...	0.048	(0.0008)	0.0011	...	...	...	...	...	50g	
CRM	C41 X GLV40A	0.0038	...	0.201	(0.0001)	0.017	<0.005	0.0009	0.049	...	0.025	<0.002	0.0051	...	...	...	...	...	50g	
CRM	C41 X GLV50A	0.0187	...	0.014	0.0138	0.076	0.020	0.0116	0.0030	...	0.162	0.0041	0.0109	...	...	...	...	...	50g	
CRM	C41 X GLV60A	0.120	...	0.475	0.0055	0.0048	0.015	0.041	0.0008	0.0014	0.011	0.0015	0.024	...	...	...	0.0030	0.0050	50g	
CRM	C41 X GLV70A	0.082	...	0.399	0.00056	0.0031	(0.0006)	0.023	0.0060	0.0025	0.0031	0.0016	0.0108	...	...	...	0.0010	(0.0001)	50g	
	C41 CG 02701	0.0030	...	...	0.0010	0.0010	...	0.00010	...	...	...	...	...	...	...	...	...	...	50g	
	C41 CG 02702	0.0142	...	...	0.0103	0.0097	...	0.00099	...	...	...	...	...	...	...	...	...	...	50g	
	C41 CG 02703	0.309	...	...	0.0733	0.0301	0.0025	0.0021	...	...	0.0106	0.0052	...	...	...	...	...	...	50g	
	C41 M BS SP-A	0.003	...	0.051	...	0.011	<0.001	<0.0005	...	...	0.099	...	...	...	...	...	...	...	50g	
	C41 M BS SP-B	0.021	...	0.141	...	0.025	<0.001	<0.002	...	...	0.061	...	...	...	...	...	...	...	50g	
	C41 M BS SP-C	0.005	...	0.185	...	0.041	<0.001	<0.0005	...	...	0.031	...	...	...	...	...	...	...	50g	
	C41 M BS SP-D	0.038	...	0.25	...	0.060	<0.001	<0.0005	...	...	0.006	...	...	...	...	...	...	...	50g	
4.2 Zn/Al		Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Cr	In	Tl	Sb	Si	Ce	La		Size	
	C42 X Z10A	0.002	<0.001	4.3	<0.001	0.002	0.002	0.003	0.001	<0.001	...	...	...	...	...	...	...	...	50g	
CRM	C42 X Z30H	0.006	0.0287	3.74	0.0048	(0.047)	0.0030	0.159	0.0102	0.0256	0.0020	...	...	0.003	0.015	(0.0003)	(0.0003)	...	50g	
	C42 X Z40A	0.01	0.05	3.25	0.003	0.005	0.003	0.057	0.017	0.014	...	...	...	...	...	...	...	...	50g	
CRM	C42 X Z40B	0.011	0.058	3.51	0.008	0.014	0.006	0.063	0.017	0.008	...	(0.0014)	(0.0026)	0.002	...	0.021	0.019	...	50g	
CRM	C42 X Z50A	0.0047	0.073	4.22	0.0021	0.029	(0.0023)	0.100	0.019	0.0070	0.0018	0.0050	0.0056	0.005	...	0.011	0.009	...	50g	
CRM	C42 X Z70A	0.0097	0.0095	4.39	0.030	0.027	0.012	0.0249	0.0067	0.0045	(0.0001)	...	...	...	0.006	0.053	0.047	...	50g	
CRM	C42 X Z80A	0.0025	0.0033	7.03	0.0003	0.013	(0.0023)	0.0215	0.0019	0.0014	(0.0002)	...	...	...	0.013	0.0081	0.0079	...	50g	
4.3 Zn/Al/Cu		Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Cr	Ti	Bi	Sb	Si	In	Tl		Size	
	C43 X Z20A	0.008	0.042	3.2	0.01	0.02	0.01	0.89	0.003	0.008	...	...	...	...	...	...	...	...	50g	
CRM	C43 X Z20K	0.0065	0.073	3.79	0.0068	0.021	0.003	1.04	0.012	0.0059	0.0021	...	(0.0022)	0.008	0.009	0.003	0.004	...	50g	
CRM	C43 X Z30L	0.0132	0.0143	3.64	0.0132	0.061	0.0125	1.59	0.0061	0.0125	0.004	...	0.018	0.003	0.005	(0.0019)	(0.0035)	...	50g	
CRM	C43 X Z40B	(0.0024)	0.043	4.76	0.0025	(0.064)	(0.0023)	3.21	0.0286	0.088	0.0063	0.0017	0.012	0.0043	(0.0065)	...	...	...	50g	
CRM	C43 X Z50A	0.0045	0.041	3.05	0.0111	0.023	0.0032	6.05	0.0021	0.0030	0.0010	0.0009	...	...	0.003	...	...	...	50g	
CRM	C43 X Z60A	0.0016	0.0256	4.02	0.0016	0.019	0.0053	2.72	0.029	0.0006	0.0006	0.0013	0.0049	0.0045	0.012	...	...	...	50g	
	C43 X Z110A	0.015	0.05	11.2	0.014	0.008	0.02	0.47	0.006	0.01	...	...	...	...	...	...	...	...	50g	
CRM	C43 X Z120D	0.0133	0.027	10.05	0.0114	0.047	0.0089	0.796	0.0035	0.0059	0.0023	0.0054	(0.002)	0.0039	(0.008)	...	...	...	50g	
CRM	C43 X Z130D	0.0125	0.0204	9.55	0.0100	0.05	0.0111	0.981	0.0109	0.0070	...	...	...	0.009	(0.0048)	...	...	...	50g	
CRM	C43 X Z140D	0.0082	0.0026	8.24	0.0067	0.015	0.0053	1.23	0.0052	0.0033	0.0046	0.0012	0.010	0.011	0.010	...	...	...	50g	
	C43 X Z150 A	0.003	0.01	8.1	0.002	0.004	0.004	1.37	0.006	0.002	...	...	...	...	...	...	...	...	50g	
CRM	C43 X Z150 C	0.0054	0.0024	7.36	0.0030	0.009	0.004	1.53	0.0019	0.0020	0.0025	0.0020	0.005	0.005	(0.011)	...	...	...	50g	
	C43 X Z210A	0.007	0.06	24.9	0.01	0.05	0.01	2.05	0.002	0.009	...	...	...	...	...	...	...	...	50g	
CRM	C43 X Z210C	0.012	0.047	23.5	0.027	0.12	0.0140	1.81	0.043	0.0104	0.0087	0.013	...	...	0.022	...	...	...	50g	
	C43 X Z230A	0.002	0.01	29.8	0.002	0.008	0.003	2.73	0.003	0.002	...	...	...	...	...	...	...	...	50g	
CRM	C43 X Z230C	0.0028	0.0133	31.4	0.0024	(0.24)	(0.002)	2.74	0.0115	0.0124	0.036	0.0026	...	...	0.061	...	...	...	50g	